

LABORATORY :- MOXLEY INDUSTRIAL CENTRE, WESTERN WAY,
ADDRESS WEDNESBURY, WEST MIDLANDS, WS10 7BG
TEL: 0121 505 4050 FAX: 0121 505 1115
www.rotechlabs.co.uk info@rotechlabs.co.uk

Test Report

Our Ref: GBW Number 110559 Issue 1 Date 08/08/2013 Page 1 of 1

A/C No: M114

Tested For:- T I MIDWOOD & COMPANY LIMITED
Green Lane
Wardle
Nantwich
Cheshire
CW5 6BJ

SALT SPRAY TESTING OF TIMCO CLASSIC SCREW SAMPLES

INTRODUCTION

The finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description: 10 off. Timco Classic Screw Samples
Finish: Stainless Steel
Specification: Salt Spray Test in accordance with ASTM.B117-11
Test Duration: 1008 Hours Salt Spray Exposure
Submitted By: Peter Owen
Customer's Order No: 4895
Sample Receipt Date: 25/06/2013

RESULTS

Salt Spray Test (ASTM B117-11 / BS EN ISO 9227:2012 / DIN.50.021-SS)

The samples were exposed to a neutral 5% Salt Spray for a test period of 1008 hours.

The samples showed no evidence of red ferrous corrosion after 1008 hours exposure.

CONCLUSION

The finish applied to the Timco Classic Screw Samples tested, **withstood** 1008 hours Salt Spray Test without the formation of red ferrous corrosion.

REPORT COMPILED BY


G B Withers
Corrosion Science
Technician

REPORT APPROVED BY


G B Withers
Corrosion Science
Technician