



LABORATORY:- MOXLEY INDUSTRIAL CENTRE, WESTERN WAY, ADDRESS WEDNESBURY, WEST MIDLANDS, WS10 7BG

TEL: 0121 505 4050 www.rotechlabs.co.uk

FAX: 0121 505 1115 info@rotechlabs.co.uk

Test Report

Our Ref: GBW	Number_	117900	Issue_	1	Date	14/03/2014	Page	1	_of_	1
A/C No: M114										
Tested For:-	T I MIDWOOD & COMPANY LIMITED Green Lane									

Wardle
Nantwich
Cheshire
CW5 6BJ

SALT SPRAY TESTING OF TIMCO ROOFING SCREW SAMPLES

INTRODUCTION

The finished samples were submitted to the laboratory for Salt Spray Corrosion Resistance Testing in accordance with the relevant specification.

RELEVANT INFORMATION

Description:

10 off. Timco Roofing Screw Samples

Finish:

Silver Ruspert

Specification:

Salt Spray Test in accordance with ASTM B117-11 Salt Spray Exposure to Red Ferrous Corrosion

Test Duration: Submitted By:

Peter Owen

Customer's Order No:

4985

Sample Receipt Date:

30/01/2014

RESULTS

Salt Spray Test (ASTM B117-11)

The samples were exposed to a neutral 5% Salt Spray for a period of 1008 hours, at which point the test ended.

The samples showed no evidence of red ferrous corrosion after 1008 hours exposure.

CONCLUSION

The finish applied to the Timco Roofing Screw Samples tested, <u>withstood</u> 1008 hours Salt Spray Test without the formation of red ferrous corrosion.

REPORT COMPILED BY

REPORT APPROVED BY

G B Withers

G B Withers Corrosion Science

Corrosion Science Technician

Technician

TESTS MARKED "NOT UKAS ACCREDITED" IN THIS REPORT/CERTIFICATE ARE NOT INCLUDED IN THE UKAS ACCREDITATION SCHEDULE FOR OUR LABORATORY.
TESTS MARKED "SC" HAVE BEEN SUBCONTRACTED.
OPINIONS AND INTERPRETATIONS EXPRESSED HEREIN ARE OUTSIDE THE SCOPE OF UKAS ACCREDITATION.
THIS TEST REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL, WITHOUT WRITTEN APPROVAL OF THE LABORATORY.
RESULTS IN THIS REPORT RELATE ONLY TO THE ITEMS TESTED.